

Characteristic	Unit	Specification	Testing Method
General Properties			
Density	g/cm ³	1.274	ISO 1183-1
Thermal Properties			
Melt Flow Rate	g/10 min.	2.54	ISO 1133-1
Glass transition point	°C	57.10	ISO 11357-1
Onset melting point	°C	144.30	ISO 11357-1
Melting point	°C	148.50	ISO 11357-1
Oxidative decomposition temperature	°C	317.50	-
Thermal decomposition temperature	°C	311.90	-
Ash content O2	Wt%	3.33	-
Ash content N2	Wt%	1.49	-
Mechanical properties			
Tensile modulus	MPa	2987.88 (± 25.98)	ISO 527-1
Tensile yield strength	MPa	69.29 (± 0.39)	ISO 527-1
Elongation at tensile yield	%	3.38 (± 0.04)	ISO 527-1
Tensile strength at break	MPa	63.48 (± 1.96)	ISO 527-1
Elongation at tensile break	%	3.9 (± 0,15)	ISO 527-1
Flexural modulus	GPa	19.43 (± 0.4)	ISO 178:2003
Flexural strength	MPa	189.81 (2.28)	ISO 178:2003
Strain at flexural yield	%	1.36 (± 0.01)	ISO 178:2003
Flexural strength at break	MPa	114.06	ISO 178:2003
Strain at flexural break	%	10.73 (± 2,12)	ISO 178:2003
Charpy impact	K J/m ²	31.387 (± 4.584)	ISO 179-1

Disclaimer: This information sheet has been created with the utmost care. Unless indicated otherwise, this sheet is solely intended to provide general information. It should not be relied on for any specific purpose and no representation or warranty is given with regards to its accuracy or completeness.