

# Material Data Sheet

## PET-G



### General Information

Extruded amorphous co-polyester Polyethylene Terephthalate Glycol (PET-G) for easy processing and high toughness. This high definition odourless filament conforms to tight diameter and ovality tolerances and enables print details with precision, good surface and high resolution. It exhibits excellent colour coverage and batch-to-batch colour consistency. PET-G is naturally UV resistant.

**3D processing method:** FFF (Fused Filament Fabrication)

**Diameter (mm):** 1,75 and 2,85

**Form:** wound on a spool (app 326/123 m per 1 kg of 1,75/2,85 mm filament)

**Diameter tolerance (mm):**  $\pm 0,05/\pm 0,06$  on 100 % of the 1,75/2,85 filament length

**Packaging:** packed in a hermetically sealed plastic bag with silica gel

**Colours** (with RAL code where applicable): Transparent, Black (9017), Dark Blue (5002), Light Blue (5015), Light Green (6018), Dark Green (6002), Red (3020), Orange (2008).

Physical Properties	Standard	Value	Unit
Density	ISO 1183	1,26-1,29	g/cm <sup>3</sup>
Melt Flow Index	ISO 1133-1 (230°C/2,16 kg)	10,8	g/10 min

Thermal Properties	Standard	Value XY (Flat)	Value	Unit
Heat Deflection Temperature	ISO-75-2 (0,45 MPa)	69,5		°C
Vicat Softening Temperature	ISO 306:2014, B/50	69,1		°C
Glass Transition Temperature	DSC (10°C/min)		82,3	°C
Melting Temperature			amorphous	°C

Mechanical Properties	Standard	Value XY (Flat)	Value Z (Up)	Unit
Tensile Modulus	ISO 527-2:2012 (1 mm/min)	2.159	2.014	MPa
Tensile Stress at Yield	ISO 527-2:2012 (50 mm/min)	54,3	41,1	MPa
Tensile Stress at Break	ISO 527-2:2012 (50 mm/min)	46,1	41,1	MPa
Elongation at Yield	ISO 527-2:2012 (50 mm/min)	3,5	2,3	%
Elongation at Break	ISO 527-2:2012 (50 mm/min)	5,8	2,3	%
Flexural Modulus	ISO 178:2019 (1 mm/min)	2.267	2.010	MPa
Flexural Strength	ISO 178:2019 (5 mm/min)	76,7	67,1	MPa
Charpy Impact Strength Notched	ISO 179-1:2011 (2,9 m/s; 0,5 J)	3,2 (C)*	2,5 (C)*	kJ/m <sup>2</sup>
Hardness	ISO 868:2004	74,4		Shore D

The tests were performed on material in black colour either on filament or 3D printed parts (XY/Flat or Z/Up). **Printing conditions (3D specimens):** Prusa i3MKS3, nozzle: 245 °C, nozzle type: brass, nozzle diameter: 0,4 mm, bed temperature: 80/85 °C, layer height 0,2 mm, infill: 100 %, active cooling fan: 30-50 %, perimeter No: 3, printing speed: 45 mm/s, chamber: closed. Printed parts were conditioned. \* C = complete break.

# Material Data Sheet

## PET-G

### Printing Conditions

---

**Processing Method:** FFF (Fused Filament Fabrication)

**Drying:** Dry at up to 60°C for up to 8 hours before printing. Use a dry-box / controlled environment during printing (e.g. relative humidity 20% or lower). Store in a sealed bag. Pre-drying of the filament reduces stringing.

**Dry box:** Recommended.

**Adhesion:** Use glue for glass bed and cool down for better part removal from.

**Nozzle Temperature (°C):** 245 ± 15. Use nozzle temperature 230 °C for less stringing.

**Speed (mm/s):** up to 180

**Bed temperature (°C):** 85 ± 10

**Bed type:** satin coated sheet, glass.

**Retraction speed (mm/s):** 45

**Retraction length (mm):** direct drive 1,2-1,4; Bowden drive (12-16)

**Active cooling (%):** 30 – 70

### Compliance

---

This material is compliant with:

- **REACH:** Regulation (EC) No 1907/2006 of the European Parliament and of the Council of 18 December 2006 concerning the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH)
- **RoHS 2:** Directive 2011/65/EU

### Notes

---

The diameter of our filament is measured with **triple axis diameter gauges** for the most precise measurement readings. This leaves less room for error and reduces the possibility of ovality deviation in comparison to both, single- and double-axis gauges. With the accuracy of ± 1 µm and resolution 0,01 µm, our laser devices take 30.000 scans per second (or 10.000 scans/second/axis). The chance of an undetectable filament over-extrusion is reduced three-fold compared to a double-axis gauge.

### Contact Information

---

Roffelsen Plastics

Lichttoren 32

5611 BJ Eindhoven

The Netherlands

Europe

Telephone / +31 (0) 492 59 2800

Email / [post@roffelsen.com](mailto:post@roffelsen.com)

Website / [www.roffelsen3d.com](http://www.roffelsen3d.com)

# Material Data Sheet

## PET-G

### Disclaimer

---

This information sheet has been created with the utmost care. Unless indicated otherwise, this sheet is solely intended to provide general information. It should not be relied on for any specific purpose and no representation or warranty is given with regards to its accuracy or completeness.